

Gypsonite Gypsum Board

No.072197

Order	Test item		Unit	Test Result	Standard Demand
1	Face quality		---	Ok	No problem
2	Tolerance of length		mm	-3	-6~-0
3	Tolerance of width		mm	-4	-5~-6
4	Tolerance of thickness		mm	-0.3	±0.6
5	Tolerance of diagonal length		mm	2	≤5
6	tapered edge width		mm	30	30~80
7	tapered edge depth		mm	0.6	0.6~1.9
8	Weight		Kg/m ²	8.6	≤12.0
9	vertical rank load	Average Value	N	572	≥500
		Min. Value		526	
10	Transverse load	Average Value	N	230	≥180
		Min. Value		225	
11	Impact resistance		—	Board back without radial crack	Board back without radial crack
12	Stickiness between the paper and material		—	ok	ok
12	Internal exposure index		—	0.1	≤1.0(A)
	External exposure index		—	0.0	≤1.3(A)

Gypsonite Gypsum Board Range

Standard Board

Length (mm)	Width (mm)	Thickness (mm)
1830/6'	1200	6.4 / ¼"
2400		8.0 / 5/16 "
2440/8'		9.0
3000	1220 / 4"	9.5 / 3/8"
3050/10'		12.0
		12.7 / ½"
3660/12'	other	15.0
other		15.9 / 5/8"
		Other



Note : Other sizes upon your detailed request

Fire Resistant Board

Length (mm)	Width (mm)	Thickness (mm)
2400	1200	12.0
		12.7 ½"
2440 / 8"	1220 / 4"	15.0
		15.9 / 5/8"



Note : Other sizes upon your detailed request

Water Resistant Board

Length (mm)	Width (mm)	Thickness (mm)
2400	1200	9.5
2440 / 8"	1220 / 4"	12.0
		12.7 / ½"

Note : Other sizes upon your detailed request

Moisture Resistant Board

Length (mm)	Width (mm)	Thickness (mm)
2400	1200	9.5
2440 / 8"	1220 / 4"	12.0
		12.7 / ½"

www.gypsonite.com

Contact Us



Emails

info@gypsonite.com

info@gypsonite.asia

Fax

+91-22-42643280

Phone

+91-22-32085151

+91-22-32269191